

## **SERVICE LIFE DESIGN - GRAPHICAL SOLUTION**

Calculations as per fib Bulletin 34 - fully probabilistic design  $\,$ 

Service Life = 100 years

Beta = 1.3, Probability of failure = 10%

Critical chloride concentration: black bars - 0.6%cem.

Initial chloride concentration: 0.1%cem.

Temperature: mean = 49.1F, std = 12.1F Exposure Zones: Buried/Submerged

Concrete Type: OPC

