

SERVICE LIFE DESIGN - GRAPHICAL SOLUTION

Calculations as per fib Bulletin 34 - fully probabilistic design
 Service Life = 100 years
 Beta = 1.3, Probability of failure = 10%
 Critical chloride concentration: black bars - 0.6%cem. Initial chloride concentration : 0.1%cem.

Temperature: mean = 49.1F, std = 12.1F
 Exposure Zones: Splash/Deicing Salts
 Concrete Type: OPC + >20%FA

