



SERVICE LIFE DESIGN - GRAPHICAL SOLUTION

Calculations as per fib Bulletin 34 - fully probabilistic design
Service Life = 100 years
Beta = 1.3, Probability of failure = 10%
Critical chloride concentration: black bars - 0.6%cm.
Initial chloride concentration : 0.1%cm.

Temperature: mean = 49.1F, std = 12.1F
Exposure Zones: Splash/Deicing Salts
Concrete Type: OPC

